



Data Sheet No: 10532  
Revision: 00  
Effective Date: 7/14/06  
Page 1 of 2

DATA SHEET			
TIVAR® Uniblend Recycled UHMW-PE			
Property	Units	Test Method	Typical Average Values
<b>Mechanical</b>			
Specific Gravity, 73° F	-	ASTM D792	.94
Tensile Strength, 73° F	psi	ASTM D638	5500
Tensile Modulus of Elasticity, 73° F	psi	ASTM D638	116000
Tensile Elongation (at break), 73° F	%	ASTM D638	250
Flexural Strength, 73° F	psi	ASTM D790	3600
Flexural Modulus of Elasticity, 73° F	psi	ASTM D790	116000
Shear Strength, 73° F	psi	ASTM D732	
Compressive Strength, 10% Deformation, 73° F	psi	ASTM D695	3300
Compressive Modulus of Elasticity, 73° F	psi	ASTM D695	100000
Hardness, Rockwell, Scale as noted, 73° F	-	ASTM D785	N/A
Hardness, Durometer, Shore "D" Scale, 73° F	-	ASTM D2240	68
Izod Impact (notched), 73° F	ft.lb./in.	ASTM D256 Type "A"	No Break
Coefficient of Friction (Dry vs. Steel) Dynamic	-	QTM 55007	.15
Limiting PV (with 4:1 safety factor applied)	ft.lbs.in. <sup>2</sup> min.	QTM 55007	2000
Sand Slurry Abrasion	1018 Steel = 100.	ASTM D4020	13
<b>Thermal</b>			
Coefficient of Linear Thermal Expansion (-40°F to 300°F)	in./in./°F	ASTM E-831 (TMA)	8.9 X 10 <sup>-5</sup>
Heat Deflection Temperature 264 psi	°F	ASTM D648	116
Tg-Glass Transition (amorphous)	°F	ASTM D3418	N/A
Melting Point (crystalline) peak	°F	ASTM D3418	260
Continuous Service Temperature in Air (Max.)(1)	°F	-	180
Thermal Conductivity	BTU in./(hr.ft. <sup>2</sup> °F)	-	

QUADRANT EPP USA, Inc. • 2120 Fairmont Avenue • P.O. Box 14235 • Reading, PA 19612-4235  
Tel: (610) 320-6660 • Fax: (610) 320-6866

Dallas, Texas (Corporate Offices)  
Houston, Texas  
Brandon, Mississippi

phone 800-782-1836 / 214-239-3870  
phone 800-282-4388 / 713-979-0660  
phone 800-457-8623 / 601-825-7919

fax 214-239-3871  
fax 713-979-0664  
fax 601-825-7109



Data Sheet No: 10532  
Revision: 00  
Effective Date: 7/14/06  
Page 2 of 2

DATA SHEET			
TIVAR® Uniblend Recycled UHMW-PE			
Property	Units	Test Method	Typical Average Values
<b>Electrical</b>			
Dielectric Strength, Short Term	Volts/mil	ASTM D149	N/A
Surface Resistivity	ohms/square	ASTM D257	> 10 <sup>15</sup>
Dielectric Constant, 10 <sup>6</sup> Hz	-	ASTM D150	N/A/
Dissipation Factor, 10 <sup>6</sup> Hz	-	ASTM D150	N/A
Flammability @ 3.1 mm (1/8 in.) (3)	-	UL94	HB
<b>Miscellaneous</b>			
Water Absorption Immersion, 24 Hours	% by wt.	ASTM D570(2)	< 0.01
Water Absorption Immersion, Saturation	% by wt.	ASTM D570(2)	< 0.01

- (1) Data represent Quadrant's estimated maximum long-term service temperature based on practical field experience.
- (2) Specimens: 1/8" thick x 2" diameter or square.
- (3) **Estimated rating based on available data.** The UL 94 Test is a laboratory test and does not relate to actual fire hazard. Contact Quadrant for specific UL "Yellow Card" recognition number.

QUADRANT EPP USA, Inc. • 2120 Fairmont Avenue • P.O. Box 14235 • Reading, PA 19612-4235  
Tel: (610) 320-6660 • Fax: (610) 320-6866

Dallas, Texas (Corporate Offices)  
Houston, Texas  
Brandon, Mississippi

phone 800-782-1836 / 214-239-3870  
phone 800-282-4388 / 713-979-0660  
phone 800-457-8623 / 601-825-7919

fax 214-239-3871  
fax 713-979-0664  
fax 601-825-7109