



New York • Philadelphia • Atlanta • Chicago • Los Angeles • Fachbach, Germany



UNINOR® PPO (Noryl®)

UNINOR PPO (blend of polyphenylene oxide and styrene) is an amorphous thermoplastic that offers a superior blend of physical strength, flame resistance, and outstanding electrical properties. Unlike many amorphous materials that tend to steadily lose strength as temperatures increase, UNINOR PPO maintains its high stiffness to temperatures in excess of 200°F. In addition, its low moisture absorption and low coefficient of thermal expansion contribute to it being one of the most dimensionally stable materials available. UNINOR PPO is an excellent V-0 UL-94 flame rating up to a thickness of 0.24".

For applications that require improved strength and stiffness, 30% glass fiber filled UNINOR Rg is available. Nytef Plastics' UNINOR PPO stock shapes machine easily and are available in a full range of heavy gauge rod, plate and tubular bar sizes.

PRODUCT ATTRIBUTES

- 230°F Continuous Use Temperature
- Excellent Strength and Rigidity, Even at Elevated Temperatures
- Low Moisture Absorption
- Superior Electrical Properties
- Rated UL V-0
- Easily Machined and Fabricated
- Glass Fiber Filled Grades for Improved Strength and Stiffness

INDUSTRIES

- Automotive
- Aircraft and Aerospace
- Appliance Manufacturing
- Electrical and Electronics Manufacturing
- Microwave Communications

APPLICATIONS

- Manifolds
- Electrical Insulators
- Electrical Connectors and Components
- Aircraft Instrumentation
- Business Equipment Housings

Nytef Plastics, Ltd. is dedicated to supplying our customers with the highest quality thermoplastic stock shapes for machining. We manufacture and stock a full line of thermoplastic materials in a wide variety of rod, plate and tubular bar sizes. In addition, we offer over 30 years of experience in the custom extrusion of application-specific and proprietary resins to meet even the most demanding performance requirements. Nytef Plastics offers full technical support for all products and is certified to ISO 9002 standards for the manufacture of extruded plastics stock shapes.

Dallas, Texas (Corporate Offices)
Houston, Texas
Brandon, Mississippi

phone 800-782-1836 / 214-239-3870
phone 800-282-4388 / 713-979-0660
phone 800-457-8623 / 601-825-7919

fax 214-239-3871
fax 713-979-0664
fax 601-825-7109



NATIONWIDE PLASTICS, INC.

The Authority on Plastics Manufacturing and Distribution

UNINOR® POLYVINYLIDENE OXIDE AND STYRENE

Property	Test Method	Units	UNINOR® Modified Polyphenylene Oxide	UNINOR® Rg 30% Glass Fiber Reinforced PPO
Mechanical				
Specific Gravity	ASTM-D792	—	1.08	1.28
Tensile Strength	ASTM-D638	psi	9,200	15,000
Tensile Elongation	ASTM-D638	%	25	5
Tensile Modulus of Elasticity	ASTM-D638	psi	370,000	
Flexural Strength	ASTM-D790	psi	14,400	23,500
Flexural Modulus of Elasticity	ASTM-D790	psi	370,000	1,040,000
Izod Notched Impact	ASTM-D256	ft.-lbs./in.	3.5	2.2
Rockwell Hardness	ASTM-D785	R or L scale	R119	L108
Thermal				
Coef. of Linear Thermal Expansion	ASTM-D696	in./in./°F	3.3 x 10 ⁻⁵	1.4 x 10 ⁻⁵
Max. Continuous Use Temp.	Nytec std.	°F	230	230
Heat Deflection Temp. @ 264 psi	ASTM-D648	°F	254	280
Melting Point	ASTM-D789	°F	490	490
Electrical				
Dielectric Strength – Short Term	ASTM-D149	volts/mil	500	550
Dielectric Constant @ 60 Hz	ASTM-D150		2.7	2.93
Dissipation Factor @ 60 Hz	ASTM-D150		0.0007	0.0009
Volume Resistivity	ASTM-D257	ohm-cm	> 10 ¹⁵	> 10 ¹⁶
Miscellaneous				
Water Absorption/24 hrs.	ASTM-D570	% weight	0.07	0.06
Flammability	UL 94		V-0	HB
Color			Black	Gray

Nytec Plastics, Ltd. believes that all physical property data and other technical information and specifications contained in this document are the best available on the product or material at the time of publication. However, this information is intended merely as a guideline to performance. Persons intending to use this information or specifications should first satisfy themselves that the products and their features/properties are suitable for their intended uses and applications and meet all appropriate safety, health or other applicable standards. Nytec Plastics, Ltd. does not guarantee the effectiveness or safety of any possible or suggested design for articles of manufacture as illustrated herein by any photograph, technical drawing or the like. It is the end user's sole responsibility to performance test the finished part in the actual or intended application. Nytec Plastics, Ltd. makes no guarantee as to this information's accuracy or completeness and will not assume any obligation or liability whatsoever for use of this information, specification or data. Nothing herein waives any of the seller's terms and conditions of sale. References to products not manufactured by Nytec Plastics, Ltd. are not intended as an endorsement of those products nor to suggest an unsuitability of other similar products. Statements containing possible suggested uses of the materials described herein are not to be construed as a license to operate under, or intended to suggest infringement of any existing patent.



NYTEF PLASTICS

800-646-9833

sales@nytec.com

New York • Philadelphia • Atlanta • Chicago • Los Angeles • Fachbach, Germany

UNINOR® is a registered trademark of NYTEF Plastics, Ltd.

©2002-Nytec Plastics 908-XM 902TC1

Dallas, Texas (Corporate Offices)
Houston, Texas
Brandon, Mississippi

phone 800-782-1836 / 214-239-3870
phone 800-282-4388 / 713-979-0660
phone 800-457-8623 / 601-825-7919

fax 214-239-3871
fax 713-979-0664
fax 601-825-7109